

# Nitrilite®

## 93-401

Clean Nitrile Glove

NBR

Nitrile

## Reliable protection for clean environments

Nitrilite® 93-401 is a clean nitrile glove with very low levels of ionic content and particles for reliable product protection. Designed for use in Class 10 (ISO 4) clean room environments.

- Compatible with Class 10 (ISO 4)
- Very low levels of ionic content and particulate for excellent product protection



### Industries

- Biotechnology Manufacturing
- Medical Device Manufacturing

### Recommended For

- Transferring liquids
- Clean room cleaning and preparing

## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

	93-401
Material	Nitrile
Color	Natural
Shape	Ambidextrous
Cuff	Beaded
Manufacturing/QMS Audit Standards	ISO 9001:2015
Regulatory/Standards Compliance	Category III, EN 420:2003 + A1:2009, EN ISO 374-1:2016, EN ISO 374-5:2016, FDA21 CFR 177-2600
Packaging	50 gloves per inner bag 2 inner bags per master polybag 10 master polybags per (1000 gloves) per liner bag
Storage	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
Country of Origin	Malaysia
Available sizes	XS (5-5.5), S (6-6.5), M (7-7.5), L (8-8.5), XL (9-9.5), XXL (10-10.5)
Powder Content	Powder-Free
External Glove Surface	Textured Fingers
Internal Glove Surface	Powder-Free, Chlorinated
Sterilization Method	Not Applicable
Cleanroom Class	Class 10/ISO 4
Shelf Life	5 Years
Tested for use with Chemotherapy Drugs	No
Protein Level	N/A: contains no natural rubber latex
Anti-static	Yes

#### PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/in)	300 / 12		EN 420/ASTM D3767
Freedom from Holes	1.5 AQL		EN 455-1/ASTM D3577
Typical Particle Count ≥0.5µm (counts / cm <sup>2</sup> )	< 400 particles / cm <sup>2</sup>		IENT-RP-CC005.4
Minimum Single Wall Palm Thickness (mm/mil)	0.11 / 4.3		EN 420/ASTM D3767
Minimum Single Wall Finger Thickness (mm/mil)	0.13 / 4.9		EN 420/ASTM D3767
Minimum Single Wall Cuff Thickness (mm/mil)	0.08 / 3.1		EN 420/ASTM D3767
	Before Ageing	During Ageing	
Ultimate tensile strength (MPa)	≥ 18	N/A	ASTM D412-06a

#### IONIC CONTENT

Concentration in µg/cm <sup>2</sup>	Typical	Concentration in µg/cm <sup>2</sup>	Typical
Calcium	0.175	Potassium	0.006
Chloride	N/A	Sodium	0.012
Lithium	0.0001	Sulphate	0.004
Magnesium	0.001	Zinc	0.017
Nitrate	0.048		

#### ORDERING INFORMATION

	SIZE	XS (5-5.5)	S (6-6.5)	M (7-7.5)	L (8-8.5)	XL (9-9.5)	XXL (10-10.5)
93-401	REORDER NO.	365757	365758	365759	365760	365761	365772

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

##### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

##### Asia Pacific Region

Ansell Global Trading Center  
T: +603 8310 6688  
F: +603 8310 6699

##### North America Region

Ansell Healthcare Products LLC  
US T: +1 800 800 0444  
US F: +1 800 800 0445  
CA T: +1-800-363-8340

##### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
T: +52 442 248 1544 / 248 3133

##### Australia

Ansell Limited  
T: +61 1800 337 041  
F: +61 1800 803 578

##### UK

Ansell Nitrilite  
T: +44 1638 663338  
F: +44 1638 668890

#### Performance Standards and Regulatory Compliance



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2021 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.