



BioClean-D Overboots - Sterile S-BDOB

Overboots - Sterile

The single use BioClean-D Disposable Overboots are constructed from antistatic low-linting CleanTough material, and feature a slip-resistant sole and tie fastenings for quick and easy donning.

Please contact Ansell Customer Service for specific chemotherapy drug permeation times and recommendations.

- Lightweight & low-linting CleanTough material
- Elasticated opening for a firm fit
- Easy tie fastenings for a secure hold on leg
- Slip-resistant sole



Industries

- Controlled and Critical Environments
- Production and Manufacturing
- Pharmaceutical Manufacturing
- Biotechnology Manufacturing
- Medical Device Manufacturing





BioClean-D Overboots - Sterile S-BDOB

TECHNICAL DATA SHEET

PRODUCT INFORMATION

	S-BDOB
Material	Polyethylene/non-woven polypropylene laminate
Color	White
Manufacturing/QMS Audit Standards	Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D
Regulatory/Standards Compliance	ASTM F739, CE 0598, EN ISO 13688:2013, EN 1149-5:2008, EN 13934-1, EN 19935-2, EN 530, EN 6530, EN 7854, EN 863, EN 9073-4, EN ISO 14325, ISO 11137-1:2006, Category III, EN 13034:2005 + A1:2009
Storage and packaging	One pair per sealed inner PE bag; 15 inner bags per sealed outer PE bag; five outer bags per lined carton (75 pairs)
Country of Origin	Malaysia
Available sizes	Universal
Sterilization Method	GAMMA irradiation (25 kGy)
Sterilization Minimum Dose	25kGy
Sterility Assurance Level	10 ⁻⁶
Cleanroom Class	Class 10/ISO 4 & EU GMP Grade A
Shelf Life	Three (3) years from date of manufacture.
Construction	Bound seams with single needle stitching
Characteristics	*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, and so are ideal for use in a static-safe environment.

MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS
Abrasion Resistance	10 to 100 cycles	1
Flex Cracking Resistance	5,000 to 15,000 cycles	3
Trapezoidal Tear Resistance Cross Direction (CD)	CD 29.3 N	2
Trapezoidal Tear Resistance Machine Direction (MD)	MD 55.5 N	3
Tensile Strength Cross Direction (CD)	CD 48 N	1
Tensile Strength Machine Direction (MD)	MD 97 N	2
Puncture Resistance	8 N	1
Repellence to Liquids – 30% H ₂ SO ₄	96.3%	3
Repellence to Liquids – 10% NaOH	97.6%	3
Repellence to Liquids – O-Xylene	95.7%	2
Repellence to Liquids – Butan-1-ol	96.6%	3
Penetration by Liquids – 30% H ₂ SO ₄	0%	3
Penetration by Liquids – 10% NaOH	0%	3
Penetration by Liquids – O-Xylene	0%	3
Penetration by Liquids – Butan-1-ol	0%	3
Seam Strength ²	70 N	2
Electrostatic Charge Half Decay Time, t ₅₀ (secs)	0.07	PASS

- 1.
2. Seam not destroyed



BioClean-D Overboots - Sterile S-BDOB

PARTICLE SHEDDING TEST RESULTS

TEST	RESULT
Particle Shedding (Helmke Drum Test)	$\geq 0.5\mu\text{m}$ (counts/min) <260

ASTM F739-12 TEST METHOD RESULTS

DRUG	Mean Breakthrough Time (MBT), Minutes Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached $0.1 \mu\text{g}/\text{cm}^2/\text{min}$
CISPLATIN	>240
CARMUSTINE	<6
CYCLOPHOSAMIDE	217 (275,162,215)
DOXORUBICINHYDROCHLORIDE	>240
5-FLUOROURACIL	>240
METHOTREXATE	>240
ETOPOSIDE	>240
PACLITAXEL	<10
THIOTEPA	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory.

SIZE CHART

Universal

ORDERING INFORMATION

	SIZE	Universal
S-BDOB	REORDER NO.	S-BDOB

For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
T: +32 (0) 2 528 74 00
F: +32 (0) 2 528 74 01

Asia Pacific Region

Ansell Global Trading Center
T: +603 8310 6688
F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC
US T: +1 800 800 0444
US F: +1 800 800 0445
CA T: +1-800-363-8340

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.
T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited
T: +61 1800 337 041
F: +61 1800 803 578

UK

Ansell Nitritex
T: +44 1638 663338
F: +44 1638 668890

Performance Standards and Regulatory Compliance



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking © 2021 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

